

## **FLEXURAL STRENGTH**

193 MPa FACT: Flexural strength can be enhanced by the addition of woven reinforcement if required.

## **SIZE & THICKNESS**

Panels can be manufactured to any length but with a width restriction of 1525mm. Standard product range can be manufactured to literally any thickness from 2mm upward.

## **TENSILE STRENGTH**

123MPa

## **TENSILE MODULUS**

7.1 GPa GRP sheet is up to seven times stronger than mild steel on a weight for weight basis.

## **THERMAL CONDUCTIVITY**

GRITTED PLATE: 0.2 w/mK

## **LOGISTICS**

Panels are usually supplied on pallets and can be delivered anywhere in the EU within approximately 10 - 14 working days under normal circumstances. Each panel can be marked with a location code and panel size on the protective covering of the goods if required.